

NWIA149199

Clear Water Base 2K Self Healing Natural Effect Soft Touch Top Coat





TECHINCAL FEATURES

- Self Healing, Natural Effect, Zero Sheen, High Transparency
- Does NOT change the Natural Color of the Wood
- Exceptional Soft Touch
- Easy to Apply, Fast Drying, Great Vertical Hang

GOOD TO KNOW



NOVOTINT

NWIA149199 can be used as a clear topcoat ONLY but can be applied to stains or pigmented base coats.



PROPER CARE

For cleaning purposes use mild soap and warm water. Furniture polishes not recommended.



WHERE TO USE

Recommended for kitchen cabinets, dining, living, and bedroom furniture.



MEETS OR EXCEEDS KCMA STANDARDS



419) 983-0007

Heat and humidity test

Cold check test

Chemical resistance test

Film swell test















361 W Longview AVE Mansfield, OH 44903 Phone: 419-983-0007 Email: info@novalkusa.com

TECHNICAL DATA SHEET

Code	Description		Date	
NWIA149199	Clear Water Base Top	Coat 2K Natural Effect, Soft Touch	07/18/2024	
Recommended Use Kitchen & Bathroom Cabinetry, Residential / Commo		Cabinetry, Residential / Commercial Wood Furnit	ure / Fixtures	
Application	1 1 1	Apply using airless, air assisted airless, or conventional spray. 2-3 coats recommended, at 5-6 Wet Mils sanding with 320 or very fine grit between coats.		
Mixing Preparatio	n I	NWIA149199 is a 2K product. Has To Be Catalyzed with NCW80 at 5% Can be Reduced up to 10% With Warm Water.		
Solids % by Wt.	36%			
Voc.	30.014 G/L			
Density	1.05			
Pot Life	3 Hour			
Shelf Life	12 Months			
Dry Times	Approximate Dryin	Approximate Drying Times At 5-6 Wet Mils		
Dust Free	30 Minutes	Note:		
Handling	60 Minutes	Drying times may vary depending on thic temperature and/or humidity. Warning: Total film thickness of the finish should nexceed 6 mils dry film.	kness applied,	
OverCoat	6 Hours			
Stackable	24 Hours		ot	

Notes And Remarks:

- Mix the product before use.
- The shelf life is 12 months if the products are stored at temperature between 41-95°F.
- The product application must be done at a temperature no less than 53°F. Coatings applied at lower temperatures will show chemical and mechanical properties lower than standard performances that can be normally achieved.
- Coating left overs (washing waters, waters from spray booths, used coatings) must be disposed according to local regulations. Never dispose residues directly into drains.
- · Application tools must be cleaned with water after use.

The data provided in this technical sheet correspond to the values and characteristics of the product offered, in relation to our skills and experience. Novalk guarantees the physical-chemical characteristics of its products, as well as their consistency. However, the responsibility for the final result of the product application is to be considered up to the user, who must ensure that the selected product corresponds to his application needs and to the type of support selected. The viscosity level of highly thixotropic products may differ from what is reported in the technical data sheet. To be considered acceptable, this value should differ by a maximum of 30% from the reported value in the technical data sheet.

Technical service tel: +419-983-0007 Email: info@novalkusa.com