

## NWIF149917B

### White Water Base 1K / 2K Tannin Blocking Primer



#### TECHINCAL FEATURES

- Exceptional Coverage, High Solids
- Fast Drying, Easy To Apply, Effective for MDF
- Excellent Sanding, Great for Vertical Hang
- To Be Used Under NOVALK Water Base Top Coats where a primer is desired.

#### GOOD TO KNOW



##### NOVOTINT

NWIF149917B can be used as a white base for the creation of pigmented colors, thanks to our Novotint Software.



##### PROPER CARE

For cleaning purposes use mild soap and warm water. Furniture polishes not recommended.



##### WHERE TO USE

Recommended for kitchen cabinets, dining, living, and bedroom furniture.



#### MEETS OR EXCEEDS KCMA STANDARDS



Heat and humidity test



Cold check test



Chemical resistance test



Film swell test



## TECHNICAL DATA SHEET

Code	Description	Date
NWIF149917B	White Water Base Tannin Blocking 1K / 2K Primer. Indoor Use.	07/18/2024

<b>Recommended Use</b>	Kitchen & Bathroom Cabinetry, Residential / Commercial Wood Furniture / Fixtures	
<b>Application</b>	<p>Apply using airless, air assisted airless, or conventional spray.</p> <p>1-2 coats at 4-5 Wet Mils can be applied under any of the NOVALK water base top coats.</p> <p>Sanding between coats using 320 or very fine grit.</p>	
<b>Mixing Preparation</b>	NWIF149917B is a ready to use product. To increase resistance of the film, use NCW80 at 5%. Agitate well.	
<b>Solids % by Wt.</b>	58%	
<b>Voc.</b>	33.0 G/L	
<b>Density</b>	1.32	
<b>Pot Life</b>	4 Hour	
<b>Shelf Life</b>	12 Months	
<b>Dry Times</b>	Approximate Drying Times At 4-5 Wet Mils	
<b>Dust Free</b>	15 Minutes	<p><b>Note:</b> Drying times may vary depending on thickness applied, temperature and/or humidity.</p> <p><b>Warning:</b> Total film thickness of the finish should not exceed 6 mils dry film.</p>
<b>Handling</b>	45 Minutes	
<b>OverCoat</b>	1-3 Hours	
<b>Sandable</b>	4 Hours	

### Notes And Remarks:

- Mix the product before use.
- The shelf life is 12 months if the products are stored at temperature between 41- 95°F.
- The product application must be done at a temperature no less than 53°F. Coatings applied at lower temperatures will show chemical and mechanical properties lower than standard performances that can be normally achieved.
- Coating left overs (washing waters, waters from spray booths, used coatings) must be disposed according to local regulations. Never dispose residues directly into drains.
- Application tools must be cleaned with water after use.

The data provided in this technical sheet correspond to the values and characteristics of the product offered, in relation to our skills and experience. Novalk guarantees the physical-chemical characteristics of its products, as well as their consistency. However, the responsibility for the final result of the product application is to be considered up to the user, who must ensure that the selected product corresponds to his application needs and to the type of support selected. The viscosity level of highly thixotropic products may differ from what is reported in the technical data sheet. To be considered acceptable, this value should differ by a maximum of 30% from the reported value in the technical data sheet.